

INDIANA LIMESTONE | FINISHES



Sawn Finish



Honed Finish



Polished Finish



Antique Brush Finish



Bushhammer Finish

ASTM SPECIFICATIONS

ASTM C 97

SPECIFIC GRAVITY: 2.27 lb/ft³

ABSORPTION: 4.84%

ASTM C 99

MODULUS OF RUPTURE

DRY CONDITION

Parallel: 784 psi

Perpendicular: 843 psi

WET CONDITION

Parallel: 727 psi

Perpendicular: 653 psi

ASTM C 170

COMPRESSIVE STRENGTH

DRY CONDITION

Parallel: 5845 psi

Perpendicular: 6581 psi

WET CONDITION

Parallel: 4693 psi

Perpendicular: 5735 psi

ASTM C 241

ABRASION RESISTANCE

DRY CONDITION

Parallel: 7.1%

Perpendicular: 7.0%

ASTM C 880

FLEXURAL STRENGTH

DRY CONDITION

Parallel: 706 psi

Perpendicular: 716 psi

WET CONDITION

Parallel: 556 psi

Perpendicular: 544 psi