

SILVERDALE | FINISHES



Sawn Finish



Honed Finish



Polished Finish



Antique Brush Finish



Bushhammer Finish

ASTM SPECIFICATIONS

ASTM C 97

DENSITY: 134.19

SPECIFIC GRAVITY: 2.151 lb/ft³

ABSORPTION: 7.51 %

ASTM C 99

MODULUS OF RUPTURE: 822 psi (5.67 MPa)

ASTM C 170

COMPRESSIVE STRENGTH: 5047 psi (34.79 MPa)

ASTM C 241

ABRASION RESISTANCE: 3.18

ASTM C 880

FLEXURAL STRENGTH: 725 psi (5.00 MPa)
